



Product Data Sheet

AGM99MF0150

General Product Description

	Min	Max	Target
Carbon ASTM D5291	99	100	<input type="checkbox"/>
Carbon Fiber: Milled			<input type="checkbox"/>
Carbon Fiber: PAN Based			<input type="checkbox"/>
Sizing: Unsized			<input type="checkbox"/>

Type: CARBON FIBERS

Typical Analysis

(U.S. Standard Test Sieves)

Resistivity Micro Ohm Meter	14
Diameter, Microns	7.4
Fiber Density g/cm ³	1.75
Fib. Tensile Strength Gpa	3.6
Youngs Modulus Gpa	207
Carbon ASTM D5291	99.5
Length (microns)	150

Test Methods

The PDS lists percentages which are only guaranteed following specific agreement between Asbury and the customer. They are listed here only to indicate approximate physical and chemical analysis. Purchasers should thoroughly test and independently verify satisfactory results before application. The user assumes the risk and liability for loss, damage, or injury arising from the application of the goods furnished.

UNCONTROLLED DOCUMENT: Prior to placing an order based on this PDS, contact the Asbury Sales Department to confirm that the information contained herein is current.

Revision Level: Issue

Revision Date:

2/25/2005

Asbury Graphite Mills, Inc.

PO Box 144 405 Old Main St.

Asbury, New Jersey 08802

Tel: (908) 537-2155 **Fax:** (908) 537-2108 **http://** www.asbury.com