



General Product Description

	Min	Max	Target
%Carbon (LOI)	80		<input type="checkbox"/>
%+100 Mesh (150 Micron)		0	<input type="checkbox"/>
%+200 Mesh (75 Micron)		0.04	<input type="checkbox"/>
%+325 Mesh (44 Micron)		0.5	<input type="checkbox"/>
%-325 Mesh (44 Micron)	99.5		<input type="checkbox"/>

Type: AMORPHOUS

Typical Analysis

(U.S. Standard Test Sieves)

%Carbon (LOI)	82.51
%+100 Mesh (150 Micron)	0
%+200 Mesh (75 Micron)	0
%+325 Mesh (44 Micron)	0.22
%-325 Mesh (44 Micron)	99.78

Test Methods

CARB	E4-1
Carbon	E4-1
MOIS	E4-7
MOIS	E4-7
MT	E3-5B
SA	E36/9
SC	E2-3
Seive Analysis	E2-2b

The PDS lists percentages which are only guaranteed following specific agreement between Cummings-Moore Graphite and the customer. They are listed here only to indicate approximate physical and chemical analysis. Purchasers should thoroughly test and independently verify satisfactory results before application. The user assumes the risk and liability for loss, damage, or injury arising from the application of the goods furnished.

UNCONTROLLED DOCUMENT: Prior to placing an order based on this PDS, contact the Asbury Sales Department to confirm that the information contained herein is current.

Revision Level: Revision 2

Revision Date:

10/10/2007

Southwestern Graphite Co., Inc.

PO Box 876 2... Route 12

DeQuincy, Louisiana 70633

Tel: (337) 786-5905

Fax: (337) 786-5907

http:// www.asbury.com