



Product Data Sheet

MICRO870

General Product Description

	Min	Max	Target
%+325 Mesh (44 Micron)	0	0.15	<input type="checkbox"/>
%Carbon (LOI)	99	100	<input type="checkbox"/>
%Moisture		0.5	<input type="checkbox"/>
MT%50 (Microns)	5	9	<input type="checkbox"/>
Surface Area m2/g	7	17	<input checked="" type="checkbox"/>

Type: FLAKE

Typical Analysis

(U.S. Standard Test Sieves)

%Carbon (LOI)	99.29
%Moisture	0.22
%+325 Mesh (44 Micron)	0.05
MT%50 (Microns)	7.73
Surface Area m2/g	10.03
Surface Area m2/g	8.99

Test Methods

The PDS lists percentages which are only guaranteed following specific agreement between Asbury and the customer. They are listed here only to indicate approximate physical and chemical analysis. Purchasers should thoroughly test and independently verify satisfactory results before application. The user assumes the risk and liability for loss, damage, or injury arising from the application of the goods furnished.

UNCONTROLLED DOCUMENT: Prior to placing an order based on this PDS, contact the Asbury Sales Department to confirm that the information contained herein is current.

Revision Level: REVISION 2

Revision Date:

6/10/1999

Asbury Graphite Mills, Inc.

PO Box 144 405 Old Main St.

Asbury, New Jersey 08802

Tel: (908) 537-2155

Fax: (908) 537-2108

http:// www.asbury.com