



Product Data Sheet MICRO890

General Product Description

	Min	Max	Target
%+325 Mesh (44 Micron)	0	0.5	<input type="checkbox"/>
%Carbon (LOI)	99	100	<input type="checkbox"/>
%Moisture	0	0.5	<input type="checkbox"/>
MT%50 (Microns)	7	11	<input type="checkbox"/>
Surface Area m2/g	5	15	<input checked="" type="checkbox"/>

Type: FLAKE

Typical Analysis

(U.S. Standard Test Sieves)

%Carbon (LOI)	99.54
%Ash	0.46
%Moisture	0.38
%+325 Mesh (44 Micron)	0.02
%-325 Mesh (44 Micron)	99.98
MT%10 (Microns)	4.76
MT%50 (Microns)	9.81
MT%90 (Microns)	17.47
MTMV (Microns)	10.72
MTSD	4.82
Surface Area m2/g	8.76

Test Methods

CARB	E4-1
MOIS	E4-7
MT	E3-5B
SA	E3-6
SC	E2-3

The PDS lists percentages which are only guaranteed following specific agreement between Asbury and the customer. They are listed here only to indicate approximate physical and chemical analysis. Purchasers should thoroughly test and independently verify satisfactory results before application. The user assumes the risk and liability for loss, damage, or injury arising from the application of the goods furnished.

UNCONTROLLED DOCUMENT: Prior to placing an order based on this PDS, contact the Asbury Sales Department to confirm that the information contained herein is current.

Revision Level: REV1

Revision Date:

3/30/2006

Asbury Graphite Mills, Inc.

RD #7, Box 1 Linde Road
Kittanning, Pennsylvania 16201

Tel: (724) 543-1343 **Fax:** (724) 543-1890 **http://** www.asbury.com